

**Company:** Hebei Meishen Technology Co.,LTD  
**Email:** hbmeishen@gmail.com  
**Telephone:** 0086-0319-3928534  
**Website:** http://magnesiumking.com

---

### Magnesium Oxide for Glass Fiber Reinforced Plastic product Details

 	<b>Name</b>	Magnesium Oxide for Glass Fiber Reinforced Plastic product
	<b>Brand</b>	Meishen
	<b>Appearance</b>	White powder
	<b>Grade</b>	Industrial Grade
	<b>Function</b>	Help to increase the brightness Thickening agent
	<b>Packing</b>	20kg net plastic woven bag with PE liner
<b>Payment</b>	L/C, T/T, D/P, PAYPAL, WESTERN UNION, MONEY GRAM	

### Active 30 Magnesium Oxide for Glass Fiber Reinforced Plastic Specification

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	92.0	Mn% $\leq$	0.003
CaO% $\leq$	1.00	Cl% $\leq$	0.20
HCl insoluble% $\leq$	0.15	Loss on ignition% $\leq$	8.0
Screenings(75 $\mu$ m)% $\leq$	0.10	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	30.1-40.0

**Company:** Hebei Meishen Technology Co.,LTD  
**Email:** hbmeishen@gmai.com  
**Telephone:** 0086-0319-3928534  
**Website:** <http://magnesiumking.com>

---

**Active 40 Magnesium Oxide for Glass Fiber Reinforced Plastic product Specification**

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	92.0	Mn% $\leq$	0.003
CaO% $\leq$	1.20	Cl% $\leq$	0.10
HCl insoluble% $\leq$	0.10	Loss on ignition% $\leq$	6.0
Screenings(75 $\mu$ m)% $\leq$	0.10	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	40.1-60.0

**Active 60 Magnesium Oxide for Glass Fiber Reinforced Plastic product Specification**

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	92.0	Mn% $\leq$	0.003
CaO% $\leq$	1.20	Cl% $\leq$	0.10
HCl insoluble% $\leq$	0.10	Loss on ignition% $\leq$	6.0
Screenings(75 $\mu$ m)% $\leq$	0.10	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	60.1-80.0

**Company:** Hebei Meishen Technology Co.,LTD  
**Email:** hbmeishen@gmail.com  
**Telephone:** 0086-0319-3928534  
**Website:** <http://magnesiumking.com>

---

**Active 80 Magnesium Oxide for Glass Fiber Reinforced Plastic product Specification**

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	90.0	Mn% $\leq$	0.003
CaO% $\leq$	1.00	Cl% $\leq$	0.20
HCl insoluble% $\leq$	0.10	Loss on ignition% $\leq$	8.0
Screenings(75 $\mu$ m)% $\leq$	0.05	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	80.1-120.0

**Active 120 Magnesium Oxide for Glass Fiber Reinforced Plastic product Specification**

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	88.0	Mn% $\leq$	0.003
CaO% $\leq$	1.00	Cl% $\leq$	0.20
HCl insoluble% $\leq$	0.10	Loss on ignition% $\leq$	10.0
Screenings(75 $\mu$ m)% $\leq$	0.05	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	120.1-150.0

**Company:** Hebei Meishen Technology Co.,LTD  
**Email:** hbmeishen@gmai.com  
**Telephone:** 0086-0319-3928534  
**Website:** <http://magnesiumking.com>

---

**Active 150 Magnesium Oxide for Glass Fiber Reinforced Plastic product Specification**

Test Item	Test Value	Test Item	Test Value
MgO% $\geq$	88.0	Mn% $\leq$	0.003
CaO% $\leq$	0.50	Cl% $\leq$	0.20
HCl insoluble% $\leq$	0.10	Loss on ignition% $\leq$	10.5
Screenings(75 $\mu$ m)% $\leq$	0.05	Bulk density% $\geq$ g/ml	0.25
Fe% $\leq$	0.05	Inhale iodine value $\geq$ (mgI <sub>2</sub> /gMgO)	150.1-180.0