



Company: Hebei Meishen Technology Co.,LTD
Email: hbmeishen@gmai.com
Telephone: 0086-0319-3928534
Website: <http://magnesiumking.com>

Silicon Steel grade Magnesium Oxide Details

 	Name	Silicon Steel grade Magnesium Oxide
	Brand	Meitai
	Appearance	White powder
	Grade	Silicon Steel Grade
	Packing	20kg net plastic woven bag with PE liner
	Payment	L/C, T/T, D/P, PAYPAL, WESTERN UNION, MONEY GRAM

1)MME Silicon Steel grade Magnesium Oxide Specification

Test Item	Test Value	Test Item	Test Value
MgO% \geq	98.0	Cl% \leq	0.03
CaO% \leq	0.50	Fe% \leq	0.05
SO ₄ % \leq	0.30	Screenings(320 μ m)% \leq	2.0
Loss on ignition% \leq	1.50	Hydration rate%	4.5

Company: Hebei Meishen Technology Co.,LTD
Email: hbmeishen@gmai.com
Telephone: 0086-0319-3928534
Website: <http://magnesiumking.com>

2)MND Silicon Steel grade Magnesium Oxide Specification

Test Item	Test Value	Test Item	Test Value
MgO% \geq	98.0	Cl% \leq	0.03
CaO% \leq	0.50	Fe% \leq	0.05
SO ₄ % \leq	0.30	Screenings(320 μ m)% \leq	2.0
Loss on ignition% \leq	1.50	Hydration rate%	3.0

3)MMZ Silicon Steel grade Magnesium Oxide Specification

Test Item	Test Value	Test Item	Test Value
MgO% \geq	98.0	Cl% \leq	0.03
CaO% \leq	0.50	Fe% \leq	0.05
SO ₄ % \leq	0.20	Screenings(320 μ m)% \leq	1.5
Loss on ignition% \leq	1.5	Hydration rate%	2.5-3.0
CAA	60-130	Viscosity	30-100
Particle size(D50) μ m	4-8		

Company: Hebei Meishen Technology Co.,LTD
Email: hbmeishen@gmail.com
Telephone: 0086-0319-3928534
Website: <http://magnesiumking.com>

4)MMG Silicon Steel grade Magnesium Oxide Specification

Test Item	Test Value	Test Item	Test Value
MgO% \geq	98.5	Cl% \leq	0.03
CaO% \leq	0.40	Fe% \leq	0.05
SO ₄ % \leq	0.20	Screenings(320 μ m)% \leq	1.0
Loss on ignition% \leq	1.4	Hydration rate%	2.5-3.0
CAA	50-100	Viscosity	60
Particle size(D50) μ m	3		

5)MMG-1 Silicon Steel grade Magnesium Oxide Specification

Test Item	Test Value	Test Item	Test Value
MgO% \geq	99.0	Cl% \leq	0.01
CaO% \leq	0.10	Fe% \leq	0.01
SO ₄ % \leq	0.10	Screenings(320 μ m)% \leq	0.1
Loss on ignition% \leq	1.0	Hydration rate%	1.5-2.0
CAA	80 \pm 10	Viscosity	80
Particle size(D50) μ m	2		